






ALUMINIUM FIBER - SOA1

dimensions



Statistics	
file	SOA1
parameter	DISTANCE
counts	35
lower bound	147.919683
upper bound	586.765200
underflow	0
in range	35
overflow	0
classes	15
modul	28.256368
min.count	0.000000
max.count	8.000000
Statistics	
minimum	147.919683
maximum	586.665200
sum	10645.030976
medianvalue	263.116631
mean	304.143742
variance	12280.068097
std.dev.	110.815469
skewness	1.003426
kurtosis	743947.964772

THICKNESS



Statistics	
file	SOA1
parameter	DISTANCE
counts	35
lower bound	26.666600
upper bound	4911.889042
underflow	0
in range	35
overflow	0
classes	15
modul	325.681496
min.count	0.000000
max.count	12.000000
Statistics	
minimum	26.666600
maximum	4911.789042
sum	100591.356932
medianvalue	2835.669504
mean	2874.038768
variance	918728.184846
std.dev.	958.503096
skewness	-0.410586
kurtosis	642001.203112

LENGTH

both the photos and the charts are only representative of a fiber sample

SOLANA s.r.l.

via Provinciale per Dolzago, 65
23848 Oggiono (LC) Italy
Ph. ++39 -0341-26.82.11
Fax. ++39 -0341-57.85.01

GREEN STEEL ESPAÑA s.l.

C/Via Augusta, 6 PRINCIPAL
08006 BARCELONA - ESPAÑA

Ph./Fax +34 93 209 21 65

GREEN STEEL POLAND Sp.Zo.o

BRZOW 56 99-423
BIELAWY PL8341781818

Ph. 0048.468382629
Fax 0048.468392013