






## BRONZE FIBER - SOB1

### dimensions



Statistics	
file	SOB1TT
parameter	DISTANCE
counts	34
lower bound	84.852502
upper bound	355.992153
underflow	0
in range	34
overflow	0
classes	15
modul	18.075370
min.count	0.000000
max.count	7.000000
Statistics	
minimum	84.852502
maximum	355.992153
sum	5958.879172
medianvalue	157.156482
mean	175.261152
variance	3974.134679
std.dev.	63.040740
skewness	1.046592
kurtosis	481779.932528

**THICKNESS**



Statistics	
file	DISTANCE
parameter	DISTANCE
counts	34
lower bound	550.815806
upper bound	5926.890825
underflow	0
in range	34
overflow	0
classes	16
modul	358.405008
min.count	0.000000
max.count	6.000000
Statistics	
minimum	550.815806
maximum	5926.890825
sum	70948.056027
medianvalue	1037.711832
mean	2086.707530
variance	675664.248894
std.dev.	1234.474507
skewness	1.161530
kurtosis	216930.050956

**LENGTH**

both the photos and the charts are only representative of a fiber sample

#### SOLANA s.r.l.

via Provinciale per Dolzago, 65  
23848 Oggiono (LC) Italy  
Ph. ++39 -0341-26.82.11  
Fax. ++39 -0341-57.85.01

#### GREEN STEEL ESPAÑA s.l .

C/Via Augusta, 6 PRINCIPAL  
08006 BARCELONA - ESPAÑA

Ph./Fax +34 93 209 21 65

#### GREEN STEEL POLAND Sp.Zo.o

BRZOWO 56 99-423  
BIELAWY PL8341781818

Ph. 0048.468382629  
Fax 0048.468392013